

Grilon AS/2

PA66

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

Product designation according to ISO 1874:

PA 66, MR 14-040 N

| Mechanical properties | dry / cond | Unit | Test Standard |
|--|--------------------|-------------------|---------------|
| Tensile Modulus | 3700 / 1700 | MPa | ISO 527-1/-2 |
| Yield stress | 95 / 60 | MPa | ISO 527-1/-2 |
| Yield strain | 4 / 12 | % | ISO 527-1/-2 |
| Nominal strain at break | 10 / >50 | % | ISO 527-1/-2 |
| Stress at break | 80 / - | MPa | ISO 527-1/-2 |
| Charpy impact strength (+23°C) | N / N | kJ/m ² | ISO 179/1eU |
| Charpy impact strength (-30°C) | N / N | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength (+23°C) | 4 / 12 | kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength (-30°C) | 4 / 4 | kJ/m ² | ISO 179/1eA |

| Mechanical properties (TPE) | dry / cond | Unit | Test Standard |
|-----------------------------|-----------------|------|---------------|
| Ball indentation hardness | 150 / 85 | MPa | ISO 2039-1 |

| Thermal properties | dry / cond | Unit | Test Standard |
|--|-----------------|-------|-----------------|
| Melting temperature (10°C/min) | 260 / - | °C | ISO 11357-1/-3 |
| Temp. of deflection under load (1.80 MPa) | 75 / - | °C | ISO 75-1/-2 |
| Temp. of deflection under load (0.45 MPa) | 225 / - | °C | ISO 75-1/-2 |
| Coeff. of linear therm. expansion (parallel) | 50 / - | E-6/K | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion (normal) | 100 / - | E-6/K | ISO 11359-1/-2 |
| Burning Behav. at thickness h | HB / - | class | IEC 60695-11-10 |
| Thickness tested | 0.8 / - | mm | IEC 60695-11-10 |
| Max. usage temperature (long term) | 80 - 100 | °C | ISO 2578 |
| Max. usage temperature (short term) | 220 | °C | EMS |


| Electrical properties | dry / cond | Unit | Test Standard |
|----------------------------|--------------------|-------|---------------|
| Volume resistivity | 1E12 / 1E11 | Ohm*m | IEC 60093 |
| Surface resistivity | - / 1E12 | Ohm | IEC 60093 |
| Electric strength | 29 / 27 | kV/mm | IEC 60243-1 |
| Comparative tracking index | - / 600 | - | IEC 60112 |

| Other properties | dry / cond | Unit | Test Standard |
|---------------------|-----------------|-------------------|----------------|
| Water absorption | 8 / - | % | Sim. to ISO 62 |
| Humidity absorption | 2 / - | % | Sim. to ISO 62 |
| Density | 1140 / - | kg/m ³ | ISO 1183 |


| Rheo/Phys properties | dry / cond | Unit | Test Standard |
|------------------------------|----------------|------|-----------------|
| Molding shrinkage (parallel) | 0.8 / - | % | ISO 294-4, 2577 |
| Molding shrinkage (normal) | 1.2 / - | % | ISO 294-4, 2577 |

Diagrams


Viscosity-shear rate




Shearstress-shear rate




Dynamic Shear modulus-temperature




Stress-strain




Stress-strain




Secant modulus-strain




Secant modulus-strain




Stress-strain (isochronous) 23 °C



Creep curve °C



Creep modulus-time 23°C



Characteristics

Processing

Injection Molding

Delivery form

Granules

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Product Attributes

Nucleated

Automotive

Hydraulic systems, Powertrain and Chassis

Electricals & Electronics

Cables & Tubes

Industry & Consumer goods

Housewares, Hydraulics & Pneumatics, Mechanical Engineering, Sports & Leisure, Tools & Accessories

Chemical Media Resistance




Acids

- ☺ Acetic Acid (5% by mass) (23°C)
- ☺ Citric Acid solution (10% by mass) (23°C)
- ☺ Lactic Acid (10% by mass) (23°C)
- ☹ Hydrochloric Acid (36% by mass) (23°C)
- ☹ Nitric Acid (40% by mass) (23°C)
- ☹ Sulfuric Acid (38% by mass) (23°C)
- ☹ Sulfuric Acid (5% by mass) (23°C)
- ☹ Chromic Acid solution (40% by mass) (23°C)




Bases

- ☹ Sodium Hydroxide solution (35% by mass) (23°C)
- ☹ Sodium Hydroxide solution (1% by mass) (23°C)
- ☹ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)


Hydrocarbons

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)





Ketones

-  Acetone (23°C)










Ethers

-  Diethyl ether (23°C)






Mineral oils

-  SAE 10W40 multigrade motor oil (23°C)
-  SAE 10W40 multigrade motor oil (130°C)
-  SAE 80/90 hypoid-gear oil (130°C)
-  Insulating Oil (23°C)










Standard Fuels

-  ISO 1817 Liquid 1 (60°C)
-  ISO 1817 Liquid 2 (60°C)
-  ISO 1817 Liquid 3 (60°C)
-  ISO 1817 Liquid 4 (60°C)
-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)

Salt solutions

-  Sodium Chloride solution (10% by mass) (23°C)
-  Sodium Hypochlorite solution (10% by mass) (23°C)
-  Sodium Carbonate solution (20% by mass) (23°C)
-  Sodium Carbonate solution (2% by mass) (23°C)
-  Zinc Chloride solution (50% by mass) (23°C)

Other

-  Ethyl Acetate (23°C)
-  Hydrogen peroxide (23°C)
-  DOT No. 4 Brake fluid (130°C)
-  Ethylene Glycol (50% by mass) in water (108°C)
-  1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)
-  Deionized water (90°C)
-  Phenol solution (5% by mass) (23°C)